

COLCLEAN SE 237L MC

TECHNICAL DATA 07-08-20

1000 Western Drive Brunswick, OH 44212 PHONE: 330/225-3200 FAX: 330/225-1499

www.columbiachemical.com

COLCLEAN SE 237L MC

LIQUID ELECTROCLEANER ADDITIVE SYSTEM

COLCLEAN SE 237L MC is a liquid builder-surfactant composition designed for use as an

additive to liquid caustic soda to form a ready to use electro cleaning

solution.

COLCLEAN SE 237L MC can be used where single tank cleaning of steel, copper, brass, and

zinc base die casting is needed.

COLCLEAN SE 237L MC is free-rinsing and contains a surfactant system designed for the

removal of many different soils.

COLCLEAN SE 237L MC can be used as a soak and an electrocleaner.

OPERATING PARAMETERS

Temperature 160° to190° F

Time 1 to 3 minutes or as required

Current Density (Anodic) 75 to 125 ASF

Adjust these conditions to provide optimum cleaning.

STEEL SUBSTRATES

COLCLEAN SE 237L MC 7 to 9% by volume (8% Optimum)

50% Liquid Caustic Soda 1.25 to 2.5% by volume (2% Optimum)

COPPER SUBSTRATES

COLCLEAN SE 237L MC 7 to 9% by volume (8% Optimum)

50% Liquid Caustic Soda 1.0 to 1.5% by volume (1.25% Optimum)

ZINC DIE-CAST SUBSTRATES

COLCLEAN SE 237L MC 7 to 9% by volume (8% Optimum)

50% Liquid Caustic Soda 0.8 to 1.2% by volume (1% Optimum)

SOLUTION MAKEUP

- 1. Charge 3/4 of the water in the tank.
- 2. Add the COLCLEAN SE 237L MC and mix.
- 3. Add liquid caustic slowly with constant agitation to prevent eruption.
- 4. While still agitating, adjust to final volume with water.
- 5. Heat the solution to operating temperature.

ANALYTICAL PROCEDURE

- 1. Obtain a sample of the COLCLEAN SE 237L MC working solution in a clean container.
- 2. Pipette a 10 ml aliquot and transfer to a titrating flask.
- 3. Add 4 to 5 drops phenolphthalein indicator.
- 4. Titrate with 1 N HCl from red to a colorless endpoint. Add a few more drops of indicator solution. If the solution turns pink, add two more drops of 1 N HCl. Repeat until the solution remains colorless when the phenolphthalein indicator is added.
- 5. Record the number of mLs required.

mLs 1 N HCl x 0.58 = % by volume concentration of the 50% Liquid Caustic.

Add appropriate ratio of COLCLEAN SE 237L MC to 50% Liquid Caustic as per initial tank.

HANDLING & STORAGE

Columbia Chemical recommends referring to the specific product Safety Data Sheets for safety, handling, and storage precautions.

NON-WARRANTY

The data contained in this bulletin is believed by Columbia Chemical Corp. to be accurate, true, and complete. Since, however, final methods of use of this product are in the hands of the customer and beyond our control, we cannot guarantee that the customer will obtain the results described in this bulletin, nor can we assume responsibility of the use of this product by the customer in any process which may infringe the patents of third parties.