



1000 Western Drive  
Brunswick, OH 44212  
PHONE: 330/225-3200  
FAX: 330/225-1499  
www.columbiachemical.com

## COLDIP TRI-V

### LIQUID TRIVALENT CHROMATE TECHNICAL DATA

12-06-11

## COLDIP TRI-V

### *CONCENTRATED LIQUID SINGLE DIP TRIVALENT CHROMATE*

COLDIP TRI-V produces a consistent blue chromate film on zinc deposits from alkaline cyanide-free zinc, cyanide zinc and chloride zinc plating processes.

COLDIP TRI-V eliminates yellow staining characteristic with hexavalent chromates on deposits from alkaline cyanide-free zinc baths.

COLDIP TRI-V baths have a longer operating life than many other trivalent chromates. In many cases, COLDIP TRI-V chromate baths can be operated for months without being dumped. Instead, they can be decanted and "charged up" once every few weeks.

COLDIP TRI-V is extremely tolerable to impurities which result in fewer rejected parts..

COLDIP TRI-V polishing action adds to brightness of parts and protects from finger prints, staining and corrosion.

COLDIP TRI-V effluent contains Trivalent Chromium, reduces waste treatment requirements.

### *GENERAL OPERATING INSTRUCTIONS*

	<u>RANGE:</u>	<u>RECOMMENDED:</u>
SOLUTION MAKEUP:	1.0% to 3% by volume	2% by volume
TEMPERATURE:	70° F to 90° F (21° to 33° C)	
DIP TIME:	10 to 35 seconds	
AGITATION:	Air or mechanical agitation recommended	
pH:	1.5 to 2.5	

### *GENERAL CONTROL AND MAINTENANCE*

COLIP TRI-V solutions are very easy to control. Generally, visual control is the most effective and easiest manner in which to monitor this chromate. As the color of the chromate finish approaches a clear white, bright appearance, an addition of COLDIP TRI-V should be made to the operating solution. These additions should be made in increments of 0.25% to 0.5% by volume, until the desired color is obtained.

A pre-dip of 0.5% Nitric Acid by volume followed by a good, fresh water rinse directly in front of the COLDIP TRI-V tank will add to the operating life of the chromate.

Although COLDIP TRI-V solutions have a great tolerance to iron and zinc, all fallen parts should be removed from the tank regularly. In doing so, the chromate will be easier to control and will last longer.

To produce the best blue color, the final hot water rinse should be between 100° to 130° and 130° F (37° to 55° C). If the final rinse is too hot, discoloration of the chromate film can occur.

## TITRATION PROCEDURE

1. Pipette a 10 ml chromate sample into a 100 ml volumetric flask. Dilute to 100 ml with distilled water and mix well.
2. Pipette 10 ml of the above diluted solution into a 250 ml Erlenmeyer flask and dilute to 100 ml with distilled water.
3. Add 5 ml 20% Sodium Hydroxide and 1 ml 35% Hydrogen Peroxide.
4. Boil solution approximately 5 minutes.
5. Slowly add 1 ml 10% Nickel Chloride Solution and continue boiling for an additional 2 minutes.
6. Cool solution to room temperature.
7. With mixing, add 10 ml Concentrated Hydrochloric Acid, 1 g Ammonium Bifluoride, 10 ml 10% Potassium Iodide and 2 ml Starch Indicator Solution.
8. Titrate with Standard 0.010 N Sodium Thiosulfate from a blue to clear-green endpoint.

*Factor:* ml 0.010 N Sodium Thiosulfate x 0.530 = % COLDIP TRI-V

## COLDIP TRI-V CYANIDE ZINC AND ALKALINE CYANIDE-FREE ZINC DEPOSITS

COLDIP TRI-V works very well on deposits from cyanide zinc baths and alkaline cyanide-free zinc baths. However, there are some applications that may require fine tuning. Even though most of today's cyanide and alkaline cyanide-free zincs are easy to rinse, some vary in caustic concentration, which plays a big roll in rinseability. There are systems that occlude a significant amount of organic in the final deposit, which can make chromating difficult. Here are some tips to obtain the most desirable chromate finishes:

- a. Make sure that there is adequate water rinsing after the zinc plating operation. Adequate means plenty of fresh water washing the work as well as adequate time in the final rinse.
- b. In some instances, a pre-dip located after the water rinses and prior to the chromate is necessary. Typically, a pre-dip of 0.25% to 0.5% by volume of Nitric Acid can be used to cut any brightener film from the surface. A good fresh water rinse should follow such a pre-dip before chromating. Failure to do so typically results in yellowing of the chromate deposit due low pH at the solution/part interface.
- c. In some instances, a pre-dip made up of 3% by volume Hydrogen Peroxide (35%) and 0.5% by volume Sulfuric Acid will be more effective at organic film removal. Again, a water rinse should follow such pre-dips before chromating.

- d. Careful testing of the finished product should be performed to determine the immersion time necessary to produce the proper chromate film. Failure to do so, could result in premature white corrosion. Typically an immersion time of 15 to 45 seconds for cyanide zincs and 30 to 40 seconds for alkaline cyanide-free zincs will provide an adequate chromate film.
- e. Hot water dips that do not exceed 130°F (55° C), as final rinses are helpful in drying the work and providing, yellow-free chromate films. This rinse must be dumped frequently, particularly on barrel lines. Hot water final rinses aid in producing bluer chromate coatings.
- f. Excessive heat in the final hot water rinse and/or drying operation can result in discoloration. Temperatures in the drying operation should be kept at a minimum, just hot enough to assure dry parts.

Adequate water rinsing cannot be over emphasized. Poor rinsing will lead to most clear chromate failures associated with cyanide zinc or alkaline cyanide-free zinc. The first rinse after plating may need to be dumped on a regular basis. The first rinse after chromating may have to be dumped on a somewhat regular basis. If the rinse after plating becomes highly alkaline, then the pH of the surface before chromating may be too highly alkaline. Such a condition results in poor polishing and a very mottled yellow deposit. If the chromate post rinse becomes overloaded with chromate, the resulting chromate film can be too thick, causing a yellowish appearance especially around holes in the part.

## **EQUIPMENT**

Chromating tanks should be constructed of stainless steel, Koroseal, PVC or rubber lined steel, or polypropylene.

## **HANDLING AND STORAGE**

COLDIP TRI-V contains trivalent chrome, strong mineral acids and oxidizers and should be stored in a cool dry area away from combustibles.

Care should be taken to avoid contact with skin or eyes. Protective clothing, rubber gloves, and goggles or face masks should be worn when handling COLDIP TRI-V.

**FREEZABILITY:** As with most chemical products, it is preferable that freezing be avoided. However if freezing should occur during transportation or storage, directions for handling the products covered in this technical data sheet are as follows:

If COLDIP TRI-V freezes, warm to 95-105F/35-41C in a warm water bath. Thoroughly mix until precipitates are completely dissolved.

## **NON-WARRANTY**

The data contained in this bulletin is believed by Columbia Chemical Corp. to be accurate, true, and complete. Since, however, final methods of use of this product are in the hands of the customer and beyond our control, we cannot guarantee that the customer will obtain the results described in this bulletin, nor can we assume any responsibility of the use of this product by the customer in any process which may infringe the patents of third parties.